



PRODUCT DESCRIPTION

ZURAFLO-TOP is a premixed, non-rusting floor hardener used to form monolithic hardened concrete floors. Special abrasive natural aggregates of Moh scale around 7 ensures of superior performance of floor surface when subjected to traffic. It provides abrasion resistant surface and inhibit rust formation.

USES

ZURAFLO-TOP is recommended for treating floor areas, where superior abrasion resistant is desired to minimise dusting, and maintenance, but not exposed to chemical attack.

Application areas include;

- ▶ Aircraft hangers
- ▶ Basement and cellars
- ▶ Mechanical workshops
- ▶ Garage for light vehicles
- ▶ Storage rooms
- ▶ Corridors and halls
- ▶ Parking areas and Loading platforms

ADVANTAGES

ZURAFLO-TOP provides a hardwearing surface on the concrete floors. This reduces the rate of abrasion from the pedestrian and vehicular movement and increases the service life of the concrete floor.

- ▶ Easy to use
- ▶ Most economical to use
- ▶ Non-metallic - Do not rust

TECHNICAL DATA

Hardness (Aggregates) | 7 Mohs Scale

DIRECTION TO USE

The design and construction of the floor should be adequate to withstand the traffic, impact and likely to be exposed

PLACING

Drier area tends to crack or delaminate, leaving less water available for subsequent shake passes. Mark the floor areas into bays of convenient size and keep the required quantity of ZURAFLO-TOP ready for each bay.

SURFACE PREPARATION

Pump, place or otherwise convey the base concrete at a slump not in excess of 120mm for a slab on grade. After the concrete has been placed, screed immediately; then bull-float/ straight edge the surface. Allow bleed water to rise to surface. Early moisture loss and rapid setting around the perimeter of the slab are typical. Monitor them closely for proper timing of the floating operations

First shake on application

After the evaporation of bleed-water, broadcast the powder evenly by hane to obtain a uniformly thick application. Do not throw or broadcast with a shovel. When the applied ZURAFLO-TOP darkens in colour indicating absorption of moisture and when the concrete has stiffened enough to prevent disk float from digging into the surface, float the treated surface using wooden hand float mechanical float fitted with float blades.

Second shake on application

Follow with the second application of ZURAFLO-TOP exactly as the first application, but while broadcasting, perpendicular direction to the first shake on is recommended. If a coarse non-slip surface is desired, start curing without any more finishing operations.

Finishing

The extend of further floating or trowelling depends upon the finish desired on the surface. Different levels of smoothness can be achieved by repeated trowelling using power trowel and gradually increasing the blade angle in each repeat trowelling.

CURING

Start curing immediately after final finishing using our membrane curing compound such as ZURACURE-WE. Barricade the area after the application of curing compound dries, cover the floor surface to protect it from staining and discolouration or physical damage.

ZURA FLOR-TOP

Metallic compound for abrasion resistant & longwearing floor surface

PACKAGING

ZURAFLOOR-TOP is supplied in 25kgs HDPE moisture resistant bags

SHELF LIFE

9 Months if kept in a dry store in the original, unopened bags. If stored at high temperatures and/or high humidity conditions the shelf life may be reduced.

COVERAGE

The rate of application of ZURAFLOOR-TOP depends on the service conditions, which the floor will be exposed to.

The recommended rates of application are as below.

For Heavy-duty traffic : 5 - 7kg/m²

For Medium duty traffic : 4 - 5kg/m²

For Light duty traffic : 3 - 4kg/m²

PRECAUTIONS

During hot, dry or windy conditions trowelling should be kept to the minimum to obtain the required finish.

All moisture used to incorporate dry-shake material must come from within the slab. Under no circumstances should water be applied to aid in the incorporation of dry shake.

If coloured floor hardener is warranted, it is strongly advised to carry out a sample area before finalization of supply order.

Clean the tools and equipment with water before the paste sticking to them hardens.

HEALTH & SAFETY

ZURAFLOOR-TOP contains Portland cement and are therefore alkaline when in contact with water.

Prolonged contact with the skin should be avoided. Any eye contamination should be washed immediately with plenty of clean water and medical advice sought.

Fire

ZURAFLOOR-TOP is non-flammable

Important: It is the Customer's responsibility to satisfy themselves by checking with the Company whether the information is still current at the time of use. The customer must be satisfied that the product is suitable for the use intended. All products comply with the properties shown on current Technical Literatures. However, **Prozura Construction Chemicals Pvt. Ltd.** does not warranty or guarantee the installation of the products as it does not have any control over installation or end use of the product. All information and particularly the recommendation relating to application and end use are given in good faith.



Prozura Construction Chemicals Pvt. Ltd.

📍 First Floor, Hague Building, 9 Sprott Road, Ballard Estate, Fort, Mumbai-400 001, (MH)

☎ +91 91520 94840 ✉ info@prozura.com 🌐 www.prozura.com